

CARBOFIL 1 is a copper coated G3Si1/ER70S-6 type solid MAG welding wire supplied both random and precision layer wound, depositing C-1.1%Mn weld metal, for welding a wide range of mild and C-Mn structural steels. Suitable for welding with CO₂ and Ar-based mixed shielding gases.

CARBOFIL 1 is a welding wire electrode used for general applications in both single- and multipass welding. Especially suited for sheet metal applications where smooth weld beads are required. Weld metal impact toughness properties are down to -40°C.

CARBOFIL 1 is available with a wide range of packaging format from few kgs for small MIG/MAG welding equipments to high-quantity (max. 550 kgs drum) robotic application.

Classification

EN ISO 14341-A: G 42 3 C G3Si1

EN ISO 14341-A: G 42 4 M G3Si1

AWS A5.18: ER 70S-6

Approvals**Grade**

ABS	33YSA
ABS	3SA
BV	SA3YM
DB	●
DNV	IIYMS

Approvals**Grade**

GL	3YS
LRS	3YS H15
RINA	3YS
TÜV	●
CE	

Chemical analysis (Typical values in %)

	C	Mn	Si	P	S
Wire	0.08	1.5	0.9	≤ 0.025	≤ 0.025
All weld metal (*)	0.08	1.1	0.6	≤ 0.025	≤ 0.025
All weld metal (**)	0.09	1.0	0.5	≤ 0.025	≤ 0.025

(*) 82% Ar+18% CO₂, (**) 100% CO₂**All-weld metal Mechanical Properties**

Heat Treatment	Yield Strength (MPa)	Tensile Strength (MPa)	Elongation A5 (%)	Impact Energy ISO - V (J)		
				+20 °C	-30 °C	-40 °C
As Welded (*)	≥ 420	500-640	≥ 24	≥ 90	≥ 70	≥ 47
As Welded (**)	≥ 420	500-640	≥ 22	≥ 70	≥ 47	

Gas test: (*) 82% Ar+18% CO₂, (**) 100% CO₂**Shielding Gas - EN ISO 14175 : M2 - C1****Materials**

S(P)235 - S(P)355; GP240; GP280

Storage

Keep dry and avoid condensation

Current condition and welding position

DC+

